

Part Number	Customer
-------------	----------

Category	Parameter	Specification	Measurement Method	
OverallWafer	1.0	Diameter	150.00 +/- 0.50 mm	
	2.0	Primary Flat Orientation	{110} +/- 1.0 degree	Wafer Vendor
	3.0	Primary Flat Length	57.50 +/- 2.50 mm	Wafer Vendor
	4.0	Secondary Flat Orientation	none	Wafer Vendor
	5.0	Overall Thickness	672.00 +/- 12.00 $\mu$ m	ADE, 100%
	6.0	Total Thickness Variation (TTV)	<5.00 $\mu$ m	Guaranteed by Process
	7.0	Bow	<80.00 $\mu$ m	ADE to ASTM F534, 100%
	8.0	Warp	<80.00 $\mu$ m	
	9.0	Edge Chips	0	Bright Light, 100% (note 2)
	10.0	Edge Exclusion	5mm	
HandleSilicon	11.0	Handle Growth Method	CZ	Wafer Vendor
	12.0	Handle Orientation	{100} +/- 1.0 degree	Wafer Vendor
	13.0	Handle Thickness	348.00 +/- 10.00 $\mu$ m	ADE, 100%
	14.0	Handle Doping Type	Any	Wafer Vendor
	15.0	Handle Dopant	Any	Wafer Vendor
	16.0	Handle Resistivity	0.005 ~ 50 Ohmcm	Wafer Vendor
	17.0	Backside Finish	Polished with lasermark and oxide.	Guaranteed by process
BuriedOxide	18.0	Oxide Type	Thermal	
	19.0	Oxide Thickness	20,000.00 +/- 1,000.00 A	Nanospec centre point, 4%
	20.0	Oxide formed on	Handle and / or device wafer	
DeviceSilicon	21.0	Device Growth Method	CZ	Wafer Vendor
	22.0	Device Orientation	{100} +/- 1.0 degree	Wafer Vendor
	23.0	Nominal Thickness	325.00 +/- 2.00 $\mu$ m	ADE single point, 100%
	24.0	Distance to device silicon edge from wafer edge	<= 2mm	Typical by Process
	25.0	Device Doping Type	Any	Wafer Vendor
	26.0	Device Dopant	Any	Wafer Vendor
	27.0	Device Resistivity	0.005 ~ 50 Ohmcm	Wafer Vendor
	28.0	Voids	none	Wafer Vendor
	29.0	Scratches	0	Bright Light, 100% (note 2)
	30.0	Haze	none	Bright Light, 100% (note 2)

Part Number	Customer
-------------	----------

Category	Parameter	Specification	Measurement Method
----------	-----------	---------------	--------------------

Shipping Details	Wafer per box :	Max 25	
	Packaging :	Taped Polypropylene Wafer Box Empak, Ultrapak, 150.00mm Antistatic Double Bagging	
	Lot Shipment Data	Device Thickness Bow / Warp Data Handle and SOI Thickness	



Explanatory Notes 1. Microscope inspection performed using microscope scan as below. 5x objective.

2. All bright light inspections performed exclude all wafer area outside the edge exclusion defined in Overall Wafer, Edge Exclusion. High intensity bright lamp inspection as per ASTM F523.

3. 9 point measurement are as shown in the diagram below:



Additional Information