

Part Number

Customer

Category	Parameter	Specification	Measurement Method
OverallWafer	1.0 Diameter	150.00 +/- 0.50 mm	WaferVendor
	2.0 Primary Flat Length	57.50 +/- 2.50 mm	Wafer Vendor
	3.0 Primary Flat Orientation	{110} +/- 1.0 degree	Wafer Vendor
	4.0 Growth Method	CZ	Wafer Vendor
	5.0 Type	Any	Wafer Vendor
	6.0 Dopant	any	Wafer Vendor
	7.0 Resistivity	1 - 100 ohm cm	Wafer Vendor
	8.0 Overall Thickness	555.00 +/- 5.00 um	Wafer Vendor
	9.0 Total Thickness Variation (TTV)	<5.00um	Guaranteed by process
	10.0 Bow	<50.00um	ADE measurement
	11.0 Warp	<50.00um	ADE measurement
	12.0 Orientation	<100> +/-1.0	Wafer Vendor
	13.0 Back Surface Quality	Polished with laser mark	Wafer Vendor
	14.0 Front Surface Quality	Prime	Wafer Vendor
	15.0 Edge Chips	None	Bright Light 100% (note 2)
HandleSilicon	16.0 Handle Thickness	555.00 +/- 5.00 um	100% ADE measurement
DeviceSilicon	17.0 Haze	None	Bright Light, 100% (note 2).
	18.0 Scratches	None	Bright Light, 100% (note 2).

Part Number	Customer
-------------	----------

Category	Parameter	Specification	Measurement Method
----------	-----------	---------------	--------------------

Shipping Details	Wafer per box :	Max 25
	Packaging :	Taped Polypropylene Wafer Box Empak, Ultrapak, 150.00mm Antistatic Double Bagging
	Lot Shipment Data	Device Thickness Bow / Warp Data Handle and SOI Thickness



Explanatory Notes 1. Microscope inspection performed using microscope scan as below. 5x objective.

2. All bright light inspections performed exclude all wafer area outside the edge exclusion defined in Overall Wafer, Edge Exclusion. High intensity bright lamp inspection as per ASTM F523.

3. 9 point measurement are as shown in the diagram below:



Additional Information